

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C09B 67/22, C09D 11/02, 5/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/26304</b> <b>(43) International Publication Date:</b> 11 May 2000 (11.05.00)
<b>(21) International Application Number:</b> PCT/US99/26245 <b>(22) International Filing Date:</b> 4 November 1999 (04.11.99)  <b>(30) Priority Data:</b> 09/185,931 4 November 1998 (04.11.98) US  <b>(71) Applicant:</b> UHLICH COLOR COMPANY, INC. [US/US]; 5620 N. Kolb Road, Tucson, AZ 85750 (US).  <b>(72) Inventor:</b> KAPOOR, Sain, D.; 11671 E. Darcy Place, Tucson, AZ 85748 (US).  <b>(74) Agents:</b> LECHTER, Michael, A. et al.; Squire, Sanders & Dempsey L.L.P., Suite 2700, Two Renaissance Square, 40 North Central Avenue, Phoenix, AZ 85004-4440 (US).		<b>(81) Designated States:</b> JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
<b>(54) Title:</b> CRYSTAL GROWTH INHIBITOR FOR AZO PIGMENTS  <b>(57) Abstract</b>  The crystal growth inhibitor is an azo compound from: (1) one or more sulfonated or carboxylated amines, and (2) one or more coupling components selected from the group consisting of acetoacetanilides, naphthanilides, pyrazalones and benzamidazoles. The crystal growth inhibitor can be produced separately and added to the coupling component prior to the coupling reaction, or it can be formed in situ with the pigment. Preferably, an improved pigment according to the invention includes 2 % to 5 % by weight of the crystal growth inhibitor. Monoazo pigments including the crystal growth inhibitor have been shown to have greatly improved gloss, transparency and tinctorial strength.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## CRYSTAL GROWTH INHIBITOR FOR AZO PIGMENTS

Field of the Invention

5 The invention relates to a crystal growth inhibitor for azo pigments, and azo pigment compositions that include the crystal growth inhibitor. Azo pigments including the crystal growth inhibitor have improved gloss, transparency, and tinting strength in various application media, including oleo resinous, aqueous and non-aqueous (such as hydrocarbon solvents).

Background of the Invention

10 Pigments are discrete colored particles which, when dispersed in the applicable media, impart color to it. The physical properties of pigments such as the particle size, size distribution, and the crystal structure are some of the parameters that determine the effectiveness and suitability of a particular pigment for a particular application, such as use in an aqueous media, non-aqueous media, or with plastics.

Azo pigments represent an important class of coloring agents used primarily in the  
15 manufacture of water-based inks, solvent-based inks, plastics, water-based paints and solvent-based paints. Some commonly utilized azo pigments are diarylide pigments including Pigment Yellow 12, Pigment Yellow 13, Pigment Yellow 14, Pigment Yellow 17 and Pigment Yellow 83. Other examples are disazo pyrazolone pigments, including Pigment Orange 13, Pigment Orange 34, Pigment Red 37, Pigment Red 38, Pigment Red 41 and Pigment Red 42.

20 Azo pigments are synthesized from various primary aromatic amines by a pigment synthesis process well known in the art, which includes the steps of diazotization and coupling. The diazotization preferably involves treating a primary aromatic amine with nitrous acid and the resulting compound is called diazonium salt. This diazonium salt is reacted with a coupling component to form the azo pigment in a reaction called a coupling reaction. Examples of coupling  
25 components are phenols, naphthols, and compounds that contain an enolizable methylene group, such as acetoacetanilides or pyrazalones.

Azo pigments, however, have deficiencies in certain applications and, in general, can be improved upon. For instance, in the graphic art industry, more specifically in multicolor printing, pigments of high color strength (i.e., high tinctorial strength) pure shade, good light fastness, and  
30 good flow properties (flow properties are also referred to as rheology) are needed. Moreover, especially in the case of yellow pigments, the ink industry has been able to obtain superior qualities in yellow pigments through the use of diarylide yellow pigments. Diarylide yellow pigments are undesirable, however, because of health hazards associated with dichlorobenzidine, which is used to manufacture the pigment and which is a carcinogen suspect. Therefore, monoazo  
35 pigments are used to avoid the health hazards associated with diarylide pigments despite the fact that monoazo dye properties are generally inferior.

One way to improve the properties of pigments is to alter their crystalline structure. It is

generally understood by those skilled in the art that pigment particles aggregate or crystallize after the pigment is formed in a pigment synthesis process. It is also known that when a pigment is dispersed in the applicable media in which it is used, to some extent, the physical act of dispersion breaks apart these crystals or particle aggregations (hereinafter referred to simply as "crystals"). If  
5 allowed to, however, the pigment will separate from the media and recrystallize into large, aggregate particles. Pigment properties are improved if crystal growth can be inhibited, either prior to the initial formation of the crystals during pigment synthesis, or prior to recrystallization in an applicable media, because smaller crystals impart better pigment properties than larger crystals.

One example of a specific pigment problem due to large crystal size is disclosed in U.S.  
10 Patent No. 4,474,609. There, the inventors explain that certain azo pigments show a certain solubility in some organic solvents or solvent-containing binding agents, which can adversely affect their applicability. For example, when certain pigments are dispersed in varnish binding agents the tinctorial strength increases at first as the dispersing period increases, but eventually levels off. Also, the tinctorial strength decreases upon storing ready-made varnish (i.e., which  
15 already includes the pigment dispersed in a media), and tinctorial strength tends to decrease more rapidly at higher temperatures because the pigment particles crystallize to form a large aggregate. The loss in tinctorial strength is in most cases accompanied by a decreasing transparency, and frequently also by an alteration of the shade.

The factor responsible for these undesirable processes in the preparation and storage of  
20 those varnishes is believed to be the recrystallization of the dispersed pigment particles in the solvents present. Owing to known physical laws, the small crystal particles having a high surface energy are dissolved, whereas the larger particles already present continue to grow, their ultimate size depending upon the solubility conditions. The resulting large crystal size leads to a loss in tinctorial strength and a reduced transparency.

U.S. Patent No. 4,474,609 also discloses a recrystallization-resistant monoazo pigment of alleged high tinctorial strength. Col 2, ll. 5-8. The monoazo pigment mixtures are obtained by coupling diazotized amines of the benzedine series onto acetoacetic acid arylamides. Col. 2, ll. 9-11. A percentage of the diazo and/or coupling component contains acid groups, preferably sulfo and/or carboxy groups. Col. 2, ll. 14-16. Subsequently, the reactive acid groups of the product  
30 obtained by the coupling are reacted with cation-active quaternary compounds, especially quaternary ammonium or phosphonium compounds. Col. 2, ll. 16-18.

The present invention differs from the prior art in that the crystal growth inhibitor has a molecular structure of such geometry, with a polar group so situated, that it efficiently inhibits the growth of large pigment crystals (i.e., large aggregates of pigment particles). More specifically,  
35 the present invention discloses crystal growth inhibitors having a molecular structure similar to that of the azo pigments with which they are used, and containing at least one acid functional group (preferably sulfonic or carboxylic). The crystal growth inhibitors can be made in situ during

synthesis of an azo pigment or added during synthesis of the pigment, preferably prior to the inception of pigment crystals.

The crystal growth inhibitor of the present invention does not utilize quaternary compounds, is a monoazo compound and covers a wide field of application, *i.e.*, it can be used with all types of azo pigments and is not limited to diarylide yellow, arylamide yellow,  $\beta$ -naphthol red or arylamide red. It results in significant improvements, such as superior gloss, tinctorial strength and transparency in products such as water-based inks, solvent flexo inks, solvent gravure inks and oleoresinous inks.

#### Summary of the Invention

Disclosed herein is a crystal growth inhibitor for use with azo pigments. Generally, the crystal growth inhibitor comprises two constituents: (1) a diazotisable aromatic amine including one or more acid groups and with or without functional groups, which is preferably one or more sulfonated and/or carboxylated amines, and (2) one or more coupling components bonded to the amines. If a sulfonated amine is used, it is preferably selected from one or more of the following: (1) aniline 3-sulfonic acid and its isomeric compounds containing other groups; (2) aniline 4-sulfonic acid and isomeric compounds containing other groups; and/or (3) aniline 2-sulfonic acid containing other groups. If a carboxylated amine is used, it is preferably selected from one or more of the following: (1) 2-amino benzoic acid and its isomeric compounds containing other groups; (2) 3-amino benzoic acid and its isomeric compounds containing other groups; and/or (3) 4-amino benzoic acid and its derivatives containing halogen, nitro, methoxy, ethoxy, or other functional groups. Any one, or any combination of, the above sulfonated or carboxylated amines may be used.

The coupling component may be one, or any combination of (1) an acetoacetanilide, (2) a naphthanilide, (3) a pyrazalone, or (4) a benzamidazalone.

The exact mechanism of how the crystal growth inhibitors disclosed herein improve pigment properties is not completely understood, and the invention is by no means limited to the mechanism by which it works. As previously discussed, however, it is known in the art that pigment particles aggregate together (or crystallize), and that relatively small crystals have superior properties than larger pigment crystals. By utilizing the crystal growth inhibitor of the present invention, the resulting pigment is believed to contain only sub-micron size crystals, which results in improved tinctorial strength, gloss and transparency.

The crystal inhibitors of the invention may be formed separately and added to the synthesizing azo pigment (preferably prior to crystal formation), or are prepared in situ during the synthesis of the pigment, so that they are present prior to crystal formation.

#### Detailed Description of the Invention

The crystal growth inhibitor disclosed herein can be used with monoazo and disazo pigments, the molecular structures and the process for making azo pigments being known to those

skilled in the art. Pigments of this type are described, for instance, in W. Herbst, K. Hunger, Industrielle Organische Pigmente, VCH-Verlag (1987), P.F. Gordon, P. Gregory, Organic Chemistry In Color (Springer-Verlog 1983); H. Zollinger, Color Chemistry (VCH Verlagsgesellschaft MBH 1987); P. Gregory, High-Technology Applications of Organic Colorants (Plenum Press 1991); and J. Griffiths, Colour and Constitution of Organic Molecules (Academic Press 1976), the disclosures of which are incorporated herein by reference.

The crystal growth inhibitor of the present invention has two components. The first is a diazotisable aromatic amine with or without functional groups and including one or more acid groups. The second is called a coupling component.

More specifically, the diazotisable aromatic amine including an acid group is preferably one or more sulfonated and/or carboxylated amines, or similar compounds, which may have one or more functional groups such as halogen, methyl, ethyl, methoxy, ethoxy, carbomethyl, carboamido, carboanilido, nitro and others. These are reacted with one or more of the compounds called coupling components, which include acetoacetanilides and their derivatives, naphthanilides and their derivatives, pyrazalones and their derivatives, and benzamidazolones and their derivatives, to form a crystal growth inhibitor according to the invention.

Some sulfonated amines that may be used to practice the invention are: (1) aniline 4-sulfonic acid, which may include one or more groups such as halogen methyl, ethyl, methoxy, ethoxy, carbomethyl, carbanido, carbonanilde and nitro; (2) aniline-2-sulfonic acid which may include one or more groups such as halogen methyl, ethyl, methoxy, ethoxy, carbomethyl, carbanido, carbonanilde and nitro; (3) aniline-3 sulfonic acid which may include one or more groups such as halogen methyl, ethyl, methoxy, ethoxy, carbomethyl, carbanido, carbonanilde and nitro. Some carboxylated amines that may be used to practice the invention are: (1) 2-amino benzoic acid which may include one or more groups such as halogen, methyl, ethyl, methoxy, ethoxy, carbomethyl, carboamido, carboamildo and nitro; (2) 3-amino benzoic acid which may include one or more groups such as halogen methyl, ethyl, methoxy, ethoxy, carbomethyl, carbanido, carbonanilde and nitro; and (3) 4-amino benzoic acid which may include one or more groups such as halogen methyl, ethyl, methoxy, ethoxy, carbomethyl, carbanido, carbonanilde and nitro.

Some coupling compounds that may be used to practice the invention are: (1) acetoacetanilides, including (a) acetoacetanilide; (b) acetoacet-o-anisidide; (c) acetoacet-p-anisidide; (d) acetoacet-o-toluidide, and (e) acetoacet-2, 5-dimethoxy-4-chloranilide; (2) naphthanilides, including: (a) naphthol AS, naphthol AS-D, naphthol AS-B, naphthol AS-BS, naphthol AS-OL, naphthol AS-KB, naphthol AS-LC, naphthol AS-CA, naphthol AS-PH and others known in the industry; (3) pyrazalones, including: (a) 3-methyl 1-phenyl pyrazalone; and (b) pyrazalone compounds, including those containing halogen, nitro, methyl, methoxy, or other groups in the benzene ring; and (4) benzamidazolones such as 3-hydroxyl-n- (2-oxo-5-

benzimidazoline) -2-naphthamide.

Further, one, or combination of, any of the above coupling components can be added to any one, or combination of, the above amines to form a crystal growth inhibitor according to the invention. The crystal growth inhibitor may be included in an azo pigment according to the invention from 0.1% to 25% by weight, but the preferred range is 2-5% by weight.

A major application of pigments made according to the invention is in the manufacture of printing inks. As explained below, printing inks including the improved pigments of the invention have much improved gloss, transparency and tinctorial strengths. The improved pigments of the present invention may also be used in paints and plastics. With regards to ink, paint and plastic, their respective formulations are disclosed in: R.H. Leach, editor, The Printing Ink Manual, Fourth Edition, Van Nostrand Reinhold (International) Co. Ltd., London (1988), particularly pages 282-591; with regard to paints: C.H. Hare, Protective Coatings, Technology Publishing Co., Pittsburgh (1994), particularly pages 63-288; and with regard to plastics: T.G. Webber, Coloring of Plastics, John Wiley & Sons, New York (1979), particularly pages 79-204. The foregoing references are hereby incorporated by reference herein for their teachings of ink, paint and plastic compositions, formulations and vehicles in which the compositions of this invention may be used.

The crystal growth inhibitor can be made in situ. Or it can be made separately and added during synthesis of the azo pigment either at the start of the pigment synthesis process, but preferably prior to crystallization of the pigment. All the constituents listed below are expressed by parts by weight.

The following examples illustrate the composition of the present invention and its methods of preparation. Unless otherwise indicated in the following examples or elsewhere in the specification or claims, all parts and percentages are by weight, temperatures are in degrees centigrade and pressures are at or near atmospheric.

Example 1: Preparation of Azo Pigment

- (a) 16.8 parts of m-nitro o-anisidine (MNOA) are dissolved in 250 parts of water containing 32.5 g 28% hydrochloric acid. The solution is cooled to 0 degrees C with ice. While stirring, 7.0 gm sodium nitrite as 10% solution in water is added. Stirring at 0 degrees C is continued until the diazotisation is complete. The excess nitrous acid is neutralized with sulfamic acid.
- (b) To 600 cc water containing 10.0 parts of caustic soda, 21.3 parts acetoacet-o-anisidide (AAOA) is added while stirring. When the solution is complete, 14 parts glacial acetic acid is added to reprecipitate AAOA.
- (c) Solution (a) is added to solution (b) over a 60-70 minute period with adequate stirring. At the end, there is preferably no reaction for diazo. The slurry is heated to boil and boiled for one hour. Then it is filtered and washed, preferably until no soluble salts are detected. This is dried with a yield of approximately 37.0 parts.

Example 2: Preparation of Crystal Growth Inhibitor in Situ

Example 1 is repeated except 2.5% of MNOA is replaced by o-nitro-aniline 4-sulfonic acid in step (a). This procedure makes approximately 2.5% by weight of crystal growth inhibitor and 97.5% by weight of pigment in situ.

Example 3: Separate Preparation of Crystal Growth Inhibitor

In a separate vessel, 0.6 parts of o-nitro-aniline 4-sulfonic acid is diazotised in the regular way and reacted (or coupled) with 0.53 grams of acetoacet-o-anisidide. These reactions are known by those skilled in the art. The resulting dye is added to step (b) in example 1 and the coupling reaction of step (c) is completed.

Comparison

The pigments prepared in Examples 1, 2 and 3 were each evaluated in the following water vehicle:

Preparation of the Water Vehicle

In a vessel, prepare:

Joncryl 61 (from SC Johnson)	=	227.0 parts
Colloid 999	=	17.0 parts
Diethylene Glycol	=	83.0 parts
Water	=	1373.0 parts

The above is mixed thoroughly. Afterwards, the pigments of Examples 1, 2 and 3 above were prepared for testing in the manner described below:

Preparation of the Inks From the Pigments of Example 1, 2 and 3

In an 8 oz. jar, prepare:

Pigment	=	15.0 grams
Water Vehicle	=	85.0 grams
Glass Beads	=	200 grams

These are mixed for 90 minutes on a Red Devil Shaker.

Results

Drawdowns of the above inks were made on Lenta form 3NT-3 using #5 Meyer Rod in accordance with the test method known by those in the art. The results are shown in the following chart:

Ink Made From The Pigment of Example:	Transparency	Gloss	Tintorial Strength
1	-	-	100%
2	+4	+4	110%
3	+5	+5	115%



Where 1 is equal; 2 is slightly; 3 is moderately; 4 is very good; and 5 is excellent: these values being understood by those skilled in the art. As can be seen, using the standard azo pigment of Example 1 as a basis, printing inks made with azo pigments including the crystal growth inhibitor of the present invention (i.e., Examples 2 and 3) have much improved transparency, gloss and tinctorial strength as compared to the same pigment without the crystal growth inhibitor (i.e., Example 1).

Having now described a preferred embodiment of the invention, deviations and modifications that do not depart from the spirit of the invention will occur to others. Thus, the invention is not limited to the foregoing description but is instead set forth in the following claims and legal equivalents thereof.

What is claimed is:

1. A crystal growth inhibitor for use with azo pigments, said crystal growth inhibitor comprising:
  - 5 (a) one or more amines including an acid functional group; and
  - (b) a coupling component bonded to said amines, said coupling component comprising one or more of the following: acetoacetanilides containing halogen, methyl, ethyl, methoxy, ethoxy, carbomethyl, carboamido, carboanilido and nitro, naphthanilides containing halogen, methyl, ethyl,  
10 methoxy, ethoxy, carbomethyl, carboamido, carboanilido and nitro, pyrazalones containing methyl, ethyl, methoxy and ethoxy, and benzamidazoles.
2. The crystal growth inhibitor of claim 1 wherein said amines are selected from the  
15 group consisting of sulfonated and carboxylated amines.
3. The crystal growth inhibitor of claim 1 wherein said amines are one or more sulfonated amines.
- 20 4. The crystal growth inhibitor of claim 1 wherein said amines are one or more carboxylated amines.
5. The crystal growth inhibitor of claim 1 wherein said amines include aniline  
4-sulfonic acid containing one or more groups such as halogen, methyl, ethyl,  
25 methoxy, ethoxy, carbomethyl, carboamido, carboanilido and nitro.
6. The crystal growth inhibitor of claim 1 wherein said amines include aniline-2-sulfonic acid containing one or more groups such as methyl, ethyl, methoxy,  
ethoxy, carbomethyl, carboamido, carboanilido and nitro.  
30
7. The crystal growth inhibitor of claim 1 wherein said amines include aniline-3-sulfonic acid containing one or more groups such as halogen, methyl, ethyl,  
methoxy, ethoxy, carbomethyl, carboamido, carboanilido and nitro.
- 35 8. The crystal growth inhibitor of claim 1 where said amines include 2-amino benzoic acid containing one or more groups such as halogen, methyl, ethyl,  
methoxy, ethoxy, carbomethyl, carboamido, carboanilido and nitro.

- 5
9. The crystal growth inhibitor of claim 1 where said amines include 3-amino benzoic acid containing one or more groups such as halogen, methyl, ethyl, methoxy, ethoxy, carbomethyl, carboamido, carboanilido and nitro.
- 10
10. The crystal growth inhibitor of claim 1 where said amines include 4-amino benzoic acid containing one or more groups such as halogen, methyl, ethyl, methoxy, ethoxy, carbomethyl, carboamido, carboanilido and nitro.
11. The crystal growth inhibitor of claim 1 wherein said coupling component includes acetoacetanilides.
12. The crystal growth inhibitor of claim 11 wherein said coupling component includes acetoacetanilide.
- 15
13. The crystal growth inhibitor of claim 11 wherein said coupling component includes acetoacet-o-anisidide.
14. The crystal growth inhibitor of claim 11 wherein said coupling component includes acetoacet-p-anisidide.
- 20
15. The crystal growth inhibitor of claim 11 wherein said coupling component includes acetoacet-o-toluidide.
- 25
16. The crystal growth inhibitor of claim 11 wherein said coupling component includes acetoacet-2, 5-dimethoxy-4-chloranilide.
17. The crystal growth inhibitor of claim 1 wherein said coupling component includes a naphthanilide.
- 30
18. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS.
19. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS-D.
- 35
20. The crystal growth inhibitor of claim 17 wherein said coupling component

includes naphthol AS-B.

21. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS-BS.

22. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS-OL.

23. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS-KB.

24. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS-LC.

25. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS-CA.

26. The crystal growth inhibitor of claim 17 wherein said coupling component includes naphthol AS-PH.

27. The crystal growth inhibitor of claim 1 wherein said coupling component includes a pyrazalone.

28. The crystal growth inhibitor of claim 27 wherein said coupling component includes 3-methyl 1-phenyl pyrazalone.

29. The crystal growth inhibitor of claim 27 wherein said coupling component includes a pyrazalone containing either a halogen, nitro, methyl or methoxy in the benzene ring.

30. The crystal growth inhibitor of claim 1 wherein said coupling component includes a benzamidazalone.

31. The crystal growth inhibitor of claim 30 wherein said coupling component includes 3 hydroxyl-n-(2-oxo-5-benzimidazoline)-2-naphthamide.

32. An improved azo pigment including:

(a) an azo pigment; and

- (b) a crystal growth inhibitor comprising:
- (i) a sulfonated or carboxylated amine, or combination thereof; and
  - (ii) a coupling component selected from the group consisting of acetoacetanilides, naphthanilides, pyrazalones and benzamidazolones.
- 5
33. The improved pigment of claim 32 wherein said azo pigment is a monoazo compound.
- 10 34. The improved pigment of claim 32 wherein said azo pigment is a disazo compound.
35. The improved pigment of claim 32 which includes 0.1% to 25% crystal growth inhibitor by weight.
- 15 36. The improved pigment of claim 32 which includes 2% to 5% crystal growth inhibitor by weight.
- 20 37. A printing ink composition comprising an ink vehicle and the improved pigment of claim 32.
38. The printing ink composition of claim 37 wherein said ink vehicle is aqueous-based.
- 25 39. A paint composition comprising a paint vehicle and the improved pigment of claim 32.

# INTERNATIONAL SEARCH REPORT

Inten. Appl. Application No  
PCT/US 99/26245

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC 7 C09B67/22 C09D11/02 C09D5/00		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) IPC 7 C09B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 21 35 468 A (CIBA-GEIGY A.G) 24 February 1972 (1972-02-24) page 1, last paragraph -page 2, paragraph 1	1-26, 32-39
Y	page 5, last paragraph -page 8, line 5; examples 3-5,9-14	1-39
Y	FR 2 084 545 A (HOECHST AG) 17 December 1971 (1971-12-17) page 2, line 1 - line 20	1-39
A	EP 0 012 944 A (HOECHST AG) 9 July 1980 (1980-07-09) abstract; examples & US 4 474 609 A cited in the application	1-39
-/-		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <span style="margin-left: 100px;"><input checked="" type="checkbox"/> Patent family members are listed in annex.</span>		
* Special categories of cited documents : <div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"A" document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search  <div style="text-align: center; font-weight: bold;">8 March 2000</div>		Date of mailing of the international search report  <div style="text-align: center; font-weight: bold;">15/03/2000</div>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax (+31-70) 340-3016		Authorized officer  <div style="text-align: center; font-weight: bold;">Dauksch, H</div>

# INTERNATIONAL SEARCH REPORT

Internal Application No

PCT/US 99/26245

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 0 039 307 A (CIBA GEIGY AG)</p> <p>4 November 1981 (1981-11-04)</p> <p>abstract</p>	1-39

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No  
PCT/US 99/26245

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 2135468 A	24-02-1972	GB 1356254 A BE 770037 A CA 962006 A CH 564067 A FR 2101733 A NL 7109790 A US 3759733 A	12-06-1974 17-01-1972 04-02-1975 15-07-1975 31-03-1972 18-01-1972 18-09-1973
FR 2084545 A	17-12-1971	CH 575447 A DE 2012153 A DK 131192 B GB 1348509 A JP 55010630 B US 3725101 A	14-05-1976 30-12-1971 09-06-1975 20-03-1974 18-03-1980 03-04-1973
EP 0012944 A	09-07-1980	DE 2854974 A AU 528230 B AU 5401879 A BR 7908330 A DK 543879 A,B, IN 152786 A JP 1628788 C JP 55084360 A JP 63042672 B US 4474609 A	10-07-1980 21-04-1983 26-06-1980 23-09-1980 21-06-1980 07-04-1984 20-12-1991 25-06-1980 24-08-1988 02-10-1984
EP 0039307 A	04-11-1981	CA 1149539 A DK 179181 A JP 56166252 A US 4334932 A	05-07-1983 24-10-1981 21-12-1981 15-06-1982